




P.T.B.-FILLER

Water-repellent jointing mortar for facing bricks



Characteristics



Ready-to-use, dry mortar, with water-repellent formulation, composed of refined and sieved sand, cement and special additives.

P.T.B.-FILLER is used for jointing all masonry made up off bricks, natural stone, etc. P.T.B.-FILLER comes in different colours which can be blended in dry condition, if necessary.

TECHNICAL CHARACTERISTICS

Corresponds to the requirements according NBN EN 13888

Flexural strenght after dry storage	≥ 2,5
Flexural strenght after freeze-thaw cycles	≥ 2,5
Compressive strenght after dry storage	≥ 15
Compressive strenght after freeze-thaw cycles	≥ 15
Shrinkage	≤ 3 mm/m
Reduced water absorption after 30 min. (CG2 W)	≤ 2 g
Reduced water absorption after 240 min. (CG2 W)	≤ 5 g

Mixing ratio	Consumption	Packaging
± 2,5 to 3,75 l water per bag of 25 kg (± 10 to 15 %)	250 g/running meter (joint 1x1 cm)	25 kg
Colours	Processing time	Application temperature
grey, white, light grey, grey-black, beige, rustic, zilvergry, light beige, shell, brick-red	Depending on the temperature humidity and used material	+ 5°C till + 30°C

P.T.B.-FILLER

Directions for use

Wet highly absorbing surfaces prior to application.
Add only ± 10 to 15 % water on the total weight of the P.T.B.-FILLER!
Always add the same quantity of water!

Remarks

- Ready-made cement mortars may, beyond our control, manifest small differences in colouring that are inherent to the cement itself and to the aggregates used. We cannot assume responsibility for such non-conformities.
- We recommend that you acquire the total quantity of product all at the same time for the same job.
- For the jointing of windows and doors we recommend our product P.T.B.-SILICONE SN.
- When pointing recently built walls, these must be at least 1 month old.
- Preferably point façades the same day in order to avoid differences in shade due to weather conditions. Always use the same quantity of mixing water.
- Maintain a width of joint of at least 1 cm.
- Before pointing stone strips, please consult us.
- Refer to 'Technische Voorlichting 208' (Technical Information Bulletin no. 208) – Pointing of masonry.

Packaging

Bags of 25 kg. Each bag contains an polythylene inner bag, that guarantees long lasting conservation.

