


 0965
POLYTECHNISCH BEDRIJF BVBA/SPRL – P.T.B.-COMPAKTUNA® INDUSTRIEPARK ZWIJNAARDE 6 9052 GENT – BELGIUM
11 004/CPR/130701 EN 934-2+A1 & 3+A1
MICROPOL® A.E.A. CLEAR Luchtbelvormer/Entraîneur d'air/Air Entraining/Luftporenbildner/ Luftindblandingsmiddel EN 934-2+A1, T.5 Plastificeerder/Luchtbelvormer//Plastifiant/Entraîneur d'air// Plasticizing/Air Entraining//Plastifizierer/Luftporenbildner// Plastificeringsmiddel/Luftindblandingsmiddel EN 934-3+A1, T.2 Chloride gehalte/Teneur en chlorure/Chloride content/ Chlorid Gehalt/Kloridindhold/ < 0,1% m/m Alkali gehalte/Teneur en alcalins/Alkali content/ Alkali Gehalt/Alkaliindhold < 0,75% m/m Corrosief gedrag / Comportement à la corrosion /Corrosion behaviour/ Korrosionsverhalten/ Korrosion adfærd: contains components only from EN 934-1 Annex A.1.



Type Standard



Type Clear



Action

1. Supplies air
2. Better workability



Why use for mortar?

1. The workability of the mortar is exceptional! It makes you save working hours.
2. All sharp sands can be processed equally easy, no longer problems with low-grade sandy clay, sand from Limbourg and the like.
3. Segregation, bleeding or precipitation is impossible: no water on the mortar and concrete; no need to stir the tubs.
4. Gain in volume by introduction of air bubbles.




Why use for concrete?

1. Allows better mixing and vibrating; no sand or gravel pockets.
2. Higher resistance against freezing and thawing.
3. Is more resistant to chemicals such as salts used to melt ice on the roads.
4. Lower water permeability than ordinary concrete.
5. Water saving: better water/cement ratio.
6. Segregation, bleeding or precipitation is impossible: no water on concrete.



Types

1. Standard
2. Type Clear



Mixing ratio	Consumption	Packaging
Add undiluted to the make-up water	mortar: max. 50 cc for 50 kg of cement concrete: max. 25 cc for 50 kg of cement	1 l (24 pcs/cardboard box), 5 l, 10 l and 25 l
Colours	Application temperature	
(Dark)brown, colourless	+ 5°C till + 30°C	

As the applications of our products are diverse, no single application guideline can be laid down. All product data reflect the state of knowledge of our products at the time of publication. Therefore all suggestions and recommendations concerning the use of our products are merely illustrative. Apply the product on a small and insignificant spot before starting to use our products to be sure the desired result is obtained. Always ask for the technical sheet of our products. Visit the website www.compaktuna.be. Consult our "technical department" which can be reached for free on the green number 0800/92279. The Dutch text shall be exclusively binding.

BVBA POLYTECHNISCH BEDRIJF is EN ISO 9001 certified | Certificat: BE 04/01432