



P.T.B.-MIX

Masonry mortar grey



0965

POLYTECHNISCH BEDRIJF BVBA/SPRL – P.T.B.-COMPAKTUNA®
INDUSTRIEPARK ZWIJNAARDE 6
9052 GENT – BELGIUM

07

017/CPR/130701

EN 998-2

P.T.B.-MIX

Droge metselmortel voor normaal gebruik/Prestatiemortel/binnen en buiten
Mortier à maçonner sec à usage courant/mortier performant/intérieur et extérieur
Trocken Mauermörtel für allgemeine Verwendung/nach Eignungsprüfung/Innen und Aussen
Dry masonry mortar for normal use/performance mortar/internal and external use
TYPE G

Druksterkte/Compression/Druckfestigkeit/Compressive strength	Klasse/Classe	M15
Afsluiting/Cisaillement/Anfangsscherfestigkeit/Initial shear strength	N/mm²	0,15 (TV)
Chloridegehalte/Teneur en Chlorures/Chloridgehalt/Contents of chloride		max. 0,02%
Brandweerstand/Résistance au feu/Brandverhalten/Reaction to fire		A1
Waterabsorptie/Absorption d'eau/Wasseraufnahme/Water absorption	kg/m²min ^{0,5}	0,19
Waterdampdoorlatendheid/Perméabilité à la vapeur d'eau/Wasserdampfdurchlässigkeit/Water vapor permeability	µ	15/35 (TV)
Thermische geleidbaarheid/Conductivité thermique/Wärmeleitfähigkeit/Thermal conductivity	W/m.K	0,83 (TV)
Volumieke massa/Masse Volumique/Dichte/Density	kg/m³	1850 +/- 50
Duurzaamheid/Durabilité/Dauerhaftigkeit/Durability		NPD



Characteristics

Ready-for use dry masonry mortar made up of purified and sifted sand, cement and aggregates of exceptional quality. Besides a highly plastic workability and a high resistance, P.T.B.-MIX has the feature that after mixing with water the mortar stays homogeneous (there will be no accumulation of water on the mortar).




Directions for use

Mix vigorously 25 kg of P.T.B.-MIX with ± 4 tot 4,5 litres of clean water.



Packaging

P.T.B.-MIX is delivered in bags of 25 kg and 10 kg. Every bag of 25 kg contains a polyethylene inner bag that guarantees long-lasting conservation.



+30°

+5°



Mixing ratio

± 4 to 4,5 l water per bag of 25 kg (± 16 %)

Consumption

Depending on the size of stone and the width of joint

Packaging

10 & 25 kg

Colours

Grey

Processing time

± 2h

Application temperature

+ 5°C till + 30°C

As the applications of our products are diverse, no single application guideline can be laid down. All product data reflect the state of knowledge of our products at the time of publication. Therefore all suggestions and recommendations concerning the use of our products are merely illustrative. Apply the product on a small and insignificant spot before starting to use our products to be sure the desired result is obtained. Always ask for the technical sheet of our products. Visit the website www.compaktuna.be. Consult our "technical department" which can be reached for free on the green number 0800/92279. The Dutch text shall be exclusively binding.

BVBA POLYTECHNISCH BEDRIJF is EN ISO 9001 certified | Certificat: BE 04/01432



P.T.B.-COMPACTUNA®
Industriepark - Zwijnaarde 6
9052 Gent - België
Tel.: +32 9 221 11 16
Fax.: +32 9 221 85 01
RPR Gent RPM
E-mail: info@compaktuna.be
Website: www.compaktuna.be
Oms groen nummer: 0800/92279