





| |
|--|
| 0615 |
| AALBORG PORLAND A/S Rørdalvej 44, P.O. Box 165 9300 Aalborg Denmark |
| 02 |
| 0615-CPR-9806 PORTLAND CEMENT CEM I 52,5R SR5 EN 197-1 Preparation of cement, mortar, grout etc. The declared performance, DOP 9806/01-DOP. |

| |
|---|
| 0965 |
| S.A. Cimenteries CBR Cementbedrijven N.V. Chaussée de la Hulpe 185 Therhulpssteenweg 185 B-1170 BRUSSELS |
| 03 |
| 0965-CPR-C0026 PORTLAND CEMENT CEM I 52,5N EN 197-1 Preparation of concrete, mortar, grout, etc. The declared performance, by levels and classes, is defined by the cement designation. |



+30°

+5°

Caractéristiques

Le P.T.B.-CIMENT est un ciment à base de clinker Portland.

- **Gris:** CEM I 52,5 N est un ciment Portland comprenant 95-100% de briques Portland. La résistance à la pression pendant 28 jours sur un mortier normalisé selon EN 197-1 (facteur eau/ciment = 0,5) s'élève au minimum à 52,5 MPa.
- **Blanc:** CEM I 52,5 R SR5. La résistance à la compression d'un mortier normalisé selon EN 197-1 (facteur eau/ciment = 0,5) après 28 jours sera de min. 52,5 MPa.

Emballage

Le P.T.B.-CIMENT est disponible en sacs de 5 kg, en gris et en blanc. Conservation: dans l'emballage d'origine fermé et dans un endroit sec: 6 mois.

