

Our technical specifications summarized :



	Aquafloor	Aquapox	Cryltane CF Finish	Cryltane DTS 20	Cryltane DTS 40	Cryltane DTS 60	Liboclean	Mixtane	Oxypaint SL Floor
Base	Water	Water	Solvent	Solvent	Solvent	Solvent	Water	Solvent	Solvent free
Gloss Gardner 60°	60	40	60	20 (± 5)	40 (± 10)	60 (± 10)	< 7	60-90	60
Density	1,33 kg/L	1,35 kg/L	1,35 kg/L	1.40 ± 0.05	1.35 ± 0.05	1.33 ± 0.05	1.21 ± 0.05	1,15 kg/L	1,49 kg/L
Potlife (at	2 h	2,5 h	6 h	± 5 h	± 6 h	± 6 h	-	6 h	40 mins
Solids content									
• In volume	49 ± 3%	50 ± 3%	58 ± 3%	60 ± 2%	60 ± 2%	62 ± 2%	40 ± 2%	44 ± 2%	100
• In weight	62 ± 3%	63 ± 3%	-	74 ± 2%	75 ± 2%	74 ± 2%	50 ± 2%	-	100
VOC (not diluted)	< 50 g/L	< 50 g/L	380 g/L	< 370 g/L	< 377 g/L	< 355 g/L	< 20 g/L	480 g/L	0 g/L
Drying times (at 20°C)									
• Dust dry	-	4 h	30 mins	30 mins	40 mins	40 mins	-	na 15 mins	< 2 h
• Tack free	5 h	6 h	2 à 3 h	3 h	5 h	4 h	30 min	na 3 h	< 10 h
• Dry	11 h	10 h	24 h	12 h	14 h	12 h	2 h	na 12 h	24 h
Recoatable after (at 20°C)	16 h	11 h	16 h	16-24 h	16-24 h	16-24 h	4 h	16 h	24 h

PROTECTION MADE EASY

Our technical specifications summarized :



	Aquafloor	Aquapox	Cryltane CF Finish	Cryltane DTS 20	Cryltane DTS 40	Cryltane DTS 60	Liboclean	Mixtane	Oxypaint SL Floor
Recommended layer thickness μm	60-80	60-80	50	60	60	60	-	60	60
Gloss and colour stability	Interior	Interior	Very good	Good	Very good	Very good	Interior	Excellent	Good
Lavability	Very good	Very good	-	-	-	-	Excellent	Excellent	Excellent
Theoretical yield (60 μm dry)	$\pm 8 \text{ m}^2/\text{L}$	$8 \text{ m}^2/\text{L}$	$6-10 \text{ m}^2/\text{L}$	$10 \text{ m}^2/\text{L}$	$10 \text{ m}^2/\text{L}$	$10 \text{ m}^2/\text{L}$	$10-12 \text{ m}^2/\text{L}$	$8-10 \text{ m}^2/\text{kg}$	$8-10 \text{ m}^2/\text{L}$
Food certificate	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
Bacteriostatic properties	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes

For a more detailed overview, please do not hesitate to ask our technical data sheets or test reports.

PROTECTION MADE EASY

